

POSITIVE LIST OSB

Date: 31.10.2024



position	Artykul prasa OSB	Article	Thickness mm	Format Press (netto) mm x mm			Format Saw mm x mm			Quantity m3	Min. order m3	Customer	Type of boards	Performance m3/h	target of performance m3/h	pressfaktor s/mm	Actual speed of the press mm/s	Type of timber Aspen/Pine	Type of resin
1	EXPRESS	41004	9,0	7520	x	2525	2500	x	1250	21 000	2000	Sales	OSB Basic	93	97	5,65	1 150	50/50	PMDI/PF
2	EXPRESS	41004	12,0	7520	x	2525	2500	x	1250	12 000	2000	Sales	OSB Basic	105	110	5,29	920	50/50	PMDI/PF
3	EXPRESS	41004	15,0	7520	x	2525	2500	x	1250	4 000	2000	Sales	OSB Basic	111	115	4,81	810	50/50	PMDI/PF
4	EXPRESS	41004	18,0	7520	x	2525	2500	x	1250	3 000	2000	Sales	OSB Basic	113	115	4,71	690	50/50	PMDI/PF
5	EXPRESS	41004	22,0	7520	x	2525	2500	x	1250	2 000	2000	Sales	OSB Basic	90	100	5,90	450	50/50	PMDI/PF
6	customer order	41004	12,0	5620	x	2525	2800	x	1250	-	300	Sales	OSB Basic	105	110	5,29	920	50/50	PMDI/PF
7	customer order	41001	9,0	7520	x	2525	2500	x	1250	5 000	1000	Sales	OSB	93	97	5,65	1 150	50/50	PMDI/PF
8	customer order	41001	12,0	7520	x	2525	2500	x	1250	1 000	500	Sales	OSB	105	110	5,29	920	50/50	PMDI/PF
9	customer order	41001	15,0	7520	x	2525	2500	x	1250	500	500	Sales	OSB	111	115	4,81	810	50/50	PMDI/PF
10	customer order	41001	18,0	7520	x	2525	2500	x	1250	500	500	Sales	OSB	113	115	4,71	690	50/50	PMDI/PF
11	customer order	41001	22,0	7520	x	2525	2500	x	1250	500	500	Sales	OSB	90	100	5,90	450	50/50	PMDI/PF
12	customer order	42151	8,5	7340	x	2465	2440	x	1220	600	50	Sales	OSB3	59	61	8,59	800	100/0	PMDI
13	customer order	42151	11,5	7340	x	2465	2440	x	1220	400	50	Sales	OSB3	62	64	8,13	625	100/0	PMDI
14	customer order	42151	14,5	7340	x	2465	2440	x	1220	4 000	50	Sales	OSB3	63	65	8,06	500	100/0	PMDI
15	customer order	42151	17,5	7340	x	2465	2440	x	1220	500	50	Sales	OSB3	63	65	8,05	415	100/0	PMDI

Prod.days: 29,0

Total: 55 000

Prod. per day: 1 897 m3

31.10.2024